

#### **Product Information:**

# **LD Filler Wet Room 626**

## Ready-mixed low-density filler for wet rooms

## **General description and application:**

LD Filler Wet Room 626 is a ready-mixed filler with high filling ratio and low density. It is extremely easy to apply and sand.

The filler is suitable in wet rooms for filling of walls and ceilings of plaster, concrete, plaster board etc.

The filler has good adhesion to difficult substrates, including ceramic tiles, high gloss paints and the like.

LD Filler Wet Room 626 can be painted with most types of paints.

The product is CE labelled according to EN 13963 and meets the requirements for use in plasterboard joints.

The product is registered in the database for construction products that can be included in the Nordic Ecolabelled construction.



## Physical / chemical data:

Filler:

Type: Low density filler based on acrylic dispersion

Colour: Light blue Consistency: Paste

Density: approx. 1,0kg/l.

Shelf life: Minimum 12 months in unopened packing if stored cool.

Protect from freezing.

Packaging:

Item no.	Size
7981	1 I.
7982	5 l.
7983	10 <i>l</i> .

Cured filler:

Paintable: Yes

Resistance: If the filler is exposed to heavy or direct water, it must be protected by a suitable paint.



## **DANA LIM** A/S

#### **Directions for use:**

Preparation: All surfaces must be clean and free from dust and loose particles. Slightly smudging or

strongly absorbent foundations must be primed with Plaster Primer 224 or Plaster Primer

Gel Extra 228 after cleaning.

Application: LD Filler Wet Room 626 is applied with a putty knife in a 0 – 3 mm layer. When filling layers

of more than 3 mm the filler must be applied over a number of times, and be almost completely dry between each filling, to reduce the risk of shrinkage or formation of cracks.

As deep holes we recommend using LD Filler Coarse 624, finishing with a layer of LD Filler

Wet Room 626.

Premature application of the next layer increases the risk of shrinkage and crack.

Spreading rate: Wide spreading: 1 m<sup>2</sup>/l. (1 mm layer thickness).

Joint filling: approx. 0,3 l/m.

Drying time: The drying time of the filler is depending on the thickness of the layer, type of surface,

temperature, humidity, ventilation etc. Under normal circumstances it is expected that the

filler is dry after 8-10 hours.

When plastering plasterboard joints, it is recommended to wait at least ½ day before further

treatment.

Cleaning: Clean skin with soap and water.

Tools are cleaned with water while the filler is still wet.

Cured filler can be removed mechanically or by soaking in water.

#### **Health and safety:**

For further information on safety, please refer to product safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75