

Product Information:

LD Filler Fine 621

Ready-mixed fine-grained low-density filler

General description and typical applications:

LD Filler Fine 621 is a ready-mixed fine-grained filler with high filling ratio and low density. It is extremely easy to apply and sand.

The filler is suitable for interior filling of walls and ceilings of plaster, concrete and plaster board / dry and heated rooms.

LD Filler Fine 621 can be painted with dispersion- and alkyd-based paints.

The product is CE labelled according to EN13963. For further information, see DOP.

The product has been tested and approved as a product with low emission according to the M1-classification.

The product is approved according to Emission EC1 plus



Physical / chemical data:

Filler:
 Type: Low density filler based on vinylacetate copolymer
 Colour: White
 Consistency: Paste
 Density: approx. 1,0 kg/liter
 Shelf life: Minimum 12 months in unopened packing if stored cool.
 Protect from freezing.

Packaging:

Item no.	Size
7962	5 ltr
7963	10 ltr

Cured filler:

Paintable: Yes
 Resistance: The filler is not water resistant.



Directions for use:

- Preparation:** *All surfaces must be clean and free from dust and loose particles. Slightly smudging or strongly absorbent foundations must be cleaned and primed with Plaster Primer 224 or Plaster Primer Gel Extra 228.*
- Application:** *LD Filler Fine 621 is applied with putty knife in a 0 – 3 mm layer. Apply several times for deep holes and allow the filler to dry between each application. As a deep-repair filler (4 – 15 mm) we recommend using LD Filler Coarse 624, finishing with a top layer of LD Filler Fine 621.*
- If the next layer is applied too soon, the risk of shrinkage and crack formation is increased.*
- Spreading rate:** *1 m²/liter (1 mm layer)
Joint filling: approx. 0,3 lit/m*
- Drying time:** *The drying time of the filler is depending on the thickness of the layer, type of surface, temperature, humidity, ventilation etc. Under normal circumstances it is expected that the filler is dry after 8-10 hours.*
- Cleaning:** *Clean tools and skin with water. Cured filler can be dissolved mechanically or by soaking in water.*

For further information, please refer to safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**