

Product Information:

Roller Filler 627

Ready-mixed filler Medium

Product description & use:

Roller Filler 627 is a ready-mixed medium graded filler, which is suitable for both roller and machine applied wide spreading and joint filling in dry interior areas.

The consistency of the filler is ideal for wide spreading of walls and ceilings, where structure from glass fibre, wallpaper or similar should be covered.

The product is easily applied with a roller. By using a wide filling knife optimal finish and a perfect filling work is achieved, where the need for sanding is reduced to a minimum.

The product is CE labelled according to EN13963. For further information, see DOP.

Roller Filler 627 meets the strict environmental and indoor air quality requirements required for the Nordic Eco label, Emission class EC1+ and M1 certifications.



Physical / chemical data:

Filler:
 Type: EVA-polymer dispersion
 Pigment/Fillers: Aluminium silicate, expanded perlite and dolomite
 Colour: Light grey
 Consistency: Paste
 Density: Approx. 1,0 kg/liter
 Shelf life: Minimum 12 months in unopened packing if stored cool.
 Protect from freezing.

Packaging:

Item no.	Size
7994215	15 lit

Cured filler:

Paintable: Yes
 Resistance: The filler is not water resistant.



Directions for use:

- Preparation:** *All surfaces must be clean and free from dust and loose particles. On porous or very absorbent surfaces priming should be carried out with Plaster Primer 224 or Plaster Primer Gel Extra 228 after cleaning.*
- Application:** *The filler is preferably applied with a longhaired painter's roller, e.g. Filler Roller. Alternatively, the filler can be spray applied with an equipment suited for spray fillers.*
- Please see the special brochure "Filling with a Roller".*
- Film thickness:** *Can be applied in layers up to 4 mm. Thick layers prolong the curing time significantly. When filling thicker layers, the filler should be applied several times, and be almost through dry between each filling.*
- Applying the next layer too soon increases the risk for shrinkage and crack formation.*
- Spreading rate:** *Wide spreading: 1 m²/lit at 1 mm layer thickness.
Joint filling: approx. 0,3 lit/m*
- Drying time:** *Depending on layer thickness, humidity and temperature. Under normal circumstances the filler can be sanded after 8 – 10 hours.*
- When joint filling on tapered edges it is strongly recommended to wait at least 12 hours before further treatment.*
- Cleaning:** *Filler on the skin can be washed off with soap and water. Clean tools with water. Dried filler can be dissolved by soaking in water.*

For further information about safety, please refer to safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**