

Product Information:

Master Filler Medium 625

Ready-mixed low-density filler**General description and applications:**

Master Filler Medium 625 is a ready-mixed filler with high filling ratio and low density. It is extremely easy to apply and sand.

The filler is suitable for indoor filling of walls and ceilings of plaster, concrete, and plasterboard in dry rooms.

Master Filler Medium 625 has a high degree of filling and minimum shrinkage. It can be painted with most types of paints.

The product is CE labelled according to EN 13963 and meets the requirements for use in plasterboard joints.

Master Filler Medium 625 meets the requirements of Emicode Class EC 1^{PLUS}.

The product is registered in the database for construction products that can be included in the Nordic Ecolabelled construction.

**Physical / chemical data:****Filler:**

Type:	Low density filler based on vinylacetate copolymer
Colour:	Gray
Consistency:	Paste
Density:	approx. 1.0 kg/l.
Shelf life:	Minimum 12 months in unopened packing if stored cool. Protect from freezing.
Packaging:	

Item no.	Size
79930	10 l.

Cured filler:

Paintable:	Yes
Resistance:	The filler is not water resistant.



Directions for use:

- Preparation:** *All surfaces must be clean and free from dust and loose particles. Slightly smudging or strongly absorbent foundations must be primed with Plaster Primer 224 or Plaster Primer Gel Extra 228 after cleaning.*
- Application:** *Master Filler Medium 625 is applied with a putty knife. When filling layers of more than 4 mm the filler must be applied over several times, and be almost completely dry between each filling, to reduce the risk of shrinkage or formation of cracks.*
- Premature application of the next layer increases the risk of shrinkage and crack.*
- Spreading rate:** *Wide spreading: 1 m²/l. (1 mm layer thickness).
Joint filling: approx. 0,3 l/m.*
- Drying time:** *The drying time of the filler is depending on the thickness of the layer, type of surface, temperature, humidity, ventilation etc. Under normal circumstances it is expected that the filler is dry after 8-10 hours.*
- When plastering plasterboard joints, it is recommended to wait at least ½ day before further treatment.*
- Cleaning:** *Clean skin with soap and water.
Tools are cleaned with water while the filler is still wet.
Cured filler can be removed mechanically or by soaking in water*

Health and safety:

For further information on safety, please refer to product safety data sheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**