

Product Information:

LD Filler Medium Extra 623

Professional ready-mixed light weight filler

General description and application:

LD Filler Medium Extra 623 is a high quality ready-mixed filler. The filler is developed for professional joint filling of plasterboards at walls and ceilings. The consistency of the product is optimized for easy application, filling, and sanding.

The filler is used indoor in dry rooms for filling of walls and ceilings of plaster, concrete and plasterboards.

LD Filler Medium Extra 623 has high filling capacity and minimum shrinkage. It can be painted with most types of paints.

The product is CE labelled according to EN 13963 and meets the requirements for use in plasterboard joints.

LD Filler Medium Extra 623 meets the strict environmental and indoor air quality requirements required for the Nordic Eco label, Emission certifications.



5097-0012

Physical / chemical data:

Filler:

Type: *Light weight filler based on vinyl acetate copolymer*
 Colour: *Light grey*
 Consistency: *Paste*
 Density: *approx. 1,0 kg/l.*
 Shelf life: *Minimum 12 months in unopened packing if stored cool. Protect from freezing.*

Packaging:

Item no.	Size
7991	1 l.
79975	5 l.
7997	10 l.

Cured filler:

Paintable: *Yes*
 Resistance: *The filler is not water resistant.*



Directions for use:

- Preparation:** *All surfaces must be clean and free from dust and loose particles. On porous or very absorbent surfaces priming should be carried out with Plaster Primer 224 or Plaster Primer Gel Extra 228 after cleaning.*
- Application:** *LD Filler Medium Extra 623 is applied with a putty knife in layers up to 4 mm. Thick layers prolong the curing time significantly. When filling thicker layers, the filler should be applied several times, and be almost through dry between each filling.*
- Applying the next layer too soon increases the risk for shrinkage and crack formation.*
- Spreading rate:** *Wide spreading: 1 m²/l. (1 mm layer thickness).
Joint filling: approx. 0,3 l/m.*
- Drying time:** *Depending on layer thickness, humidity, and temperature. Under normal circumstances the filler can be sanded after 8 – 10 hours.*
- When plastering plasterboard joints, it is recommended to wait at least ½ day before further treatment.*
- Cleaning:** *Clean skin with soap and water.
Tools are cleaned with water while the filler is still wet.
Cured filler can be removed mechanically or by soaking in water.*

Health and safety:

For further information on safety, please refer to product safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**