

Product Information:

LD Filler Fine 621

Ready-mixed fine-grained low-density filler

General description and application:

LD Filler Fine 621 is a ready-mixed fine-grained filler with high filling ratio and low density. It is extremely easy to apply and sand.

The filler is suitable for interior filling of walls and ceilings of plaster, concrete, and plasterboard in dry rooms.

LD Filler Fine 621 can be painted with most types of paints.

The product is CE labelled according to EN 13963 and meets the requirements for use in plasterboard joints.

LD Filler Fine 621 meets the requirements of Emission Class EC 1 PLUS.

The product is registered in the database for construction products that can be included in the Nordic Ecolabelled construction.



Physical / chemical data:

Filler:
 Type: Low density filler based on vinylacetate copolymer
 Colour: White
 Consistency: Paste
 Density: Approx. 1,0 kg/l.
 Shelf life: Minimum 12 months in unopened packing if stored cool. Protect from freezing.

Packaging:

Item no.	Size
7962	5 l.
7963	10 l.

Cured filler:
 Paintable: Yes
 Resistance: The filler is not water resistant.



Directions for use:

- Preparation:** *All surfaces must be clean and free from dust and loose particles. Slightly smudging or strongly absorbent foundations must be cleaned and primed with Plaster Primer 224 or Plaster Primer Gel Extra 228.*
- Application:** *LD Filler Fine 621 is applied with putty knife in a 0 – 3 mm layer. Apply several times for deep holes and allow the filler to dry between each application. As a deep-repair filler (4 – 15 mm) we recommend using LD Filler Coarse 624, finishing with a top layer of LD Filler Fine 621.*
- If the next layer is applied too soon, the risk of shrinkage and crack formation is increased.*
- Spreading rate:** *Wide spreading: 1 m²/l. (1 mm layer thickness)
Joint filling: approx. 0,3 l/m.*
- Drying time:** *The drying time of the filler is depending on the thickness of the layer, type of surface, temperature, humidity, ventilation etc. Under normal circumstances it is expected that the filler is dry after 8-10 hours.*
- When plastering plasterboard joints, it is recommended to wait at least ½ day before further treatment.*
- Cleaning:** *Clean skin with soap and water.
Tools are cleaned with water while the filler is still wet.
Cured filler can be removed mechanically or by soaking in water*

Health and safety:

For further information on safety, please refer to product safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**