



TECHNICAL DATASHEET

Wood adhesive for furniture manufacturing

DANAFIX

Product:
D-coll 2211

Date of issue: 05.09.2018
(Replaces: 10.09.2013)

Company DANA LIM A/S
Københavnsvej 220, DK-4600 Køge

Ph.: 56 64 00 70, Fax.: 56 64 00 90, www.danalim.dk
Technical Service Ph.: 56 64 00 75

Prepared by: Bo Brehmer

Product Description and Application:

D-coll 2211 is suitable for tenoning, assembling, sealing, edge gluing and blocks gluing in the wood working industry. The adhesive has short pressing time and is excellent for hot gluing in HF-press and hot press. The adhesive has gap filling properties and gives a tough/elastic glue line.

D-coll 2211 is only recommended for indoor using.

Article number.

20 kg bucket.....	ZVF2211SP20
120 kg drum.....	ZVF2211F120
650 kg container:.....	6050396

Physical / Chemical Properties:

Adhesive:	2211
Type:.....	Water based PVAc-dispersion
Colour:.....	White
Solid content [%]:.....	47
Viscosity (Brookf.RVF, 20 rpm) [cP]:.....	10.500
Density [kg/ltr.]:.....	1,1
pH:.....	4 – 6
Shelf life:.....	Minimum 12 months in unopened packing if stored cool.

Cured joint:

Colour:.....	Matt transparent
--------------	------------------

Directions for use:

Preparation:	Both surfaces must be clean, dry and well adjusted. Optimum results are obtained with newly worked wood.
Application:	The adhesive is applied on one surface. When bonding hard woods, two-sided application is recommended, as well as increasing assembly time and pressing time.
Wood moisture content:	8 - 14 %
Amount of glue:	150-250 g/m ² depending on the surfaces and required open time.
Application temperature:	12 -70 °C
Open assembly time: 20 °C, 50 % RH pine, 9 % moisture	6-11 min. Absorbent materials, less amount of glue, low moisture content in material and air and ventilation will influence the open time.
Pressure:	Soft wood as e.g. conifer wood 0,6-0,8 MPa (6-8 kp/cm ²) Hard wood as e.g. deciduous wood 1,0-1,2 MPa (10-12 kp/cm ²)
Pressure times, pine approx. 50 % RH, approx. 9 % moisture content of the wood	2-5 min. at 20 °C. 1-2 min. at 50-60 °C. Pressure times should be increased for hard woods, two-sided application, higher humidity of the air and higher moisture content of the wood. Full strength is usually obtained after 24 hours.
Cleaning:	Wet uncured adhesive can be removed with water. Cured adhesive can only be removed by soaking in lukewarm water or with the use of organic solvents (ex. acetone).
Storage:	Adhesive should be stored cool (max. 20 °C) in tightly closed packing. Must be protected from frost.

All information's are meant as a guideline. Sufficient test should be carried out to determine final working condition.

Safety:

Hazard Symbols: None
Risk and Safety phrases: None

For further information concerning safety, refer to safety Datasheet.

Further information:

DANA LIM offers a range of adhesives for professionals:

100-series: Upholstering adhesives
200-series: Flooring adhesives
300-series: Wall adhesives
400-series: Wood adhesives
500-series: Sealants & PU-foams
600-series: Building-additives, fillers etc.
700-series: Paper-, packaging- and newspaper adhesives
800-series: Hot melt
900-series: Cleaning-, release agents and hardeners.

The information and data contained in this data sheet are based on extensive laboratory testing and our practical experiences, and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this technical data sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.