

Product Information:

Contact Hardener 924

Increase the heat resistance of contact adhesive

General description and typical applications:

Contact Hardener 924 is added to contact adhesive 281 and transparent contact adhesive 284 to increase the heat resistance up to approx. 150 °C (depends on strength requirements).



Contact Hardener 924 is added to contact adhesive 281 & transparent contact adhesive 284 to increase heat resistance up to 150 °C (depends on strength requirements)

Physical / chemical properties:

Hardener:

Type:

Isocyanate hardener

Colour:

Yellowish

Consistency:

Liquid

Shelf life:

Minimum 12 months in unopened packaging if stored cool. Protect from freezing.

Packaging:

Art.no.	Size
3511	50 g bottle
3513	250 g bottle



Directions for use:

Application: 5 g of contact hardener 924 is added per 100 g of adhesive while stirring carefully.

Pot life: Pot life after adding the hardener, about 1 day

Also refer to Product Information Sheet for each type of adhesive.

Safety:

Contains: Isocyanater (Tris(p-isocyanatophenyl)thiophosphate). See manufacturer's instructions

Hazard symbols: F, highly flammable
Xn, harmful

Risk & Safety phrases: irritating to eyes
May cause sensitisation by inhalation
Repeated exposure may cause skin dryness
Vapours may cause drowsiness and dizziness
Keep out of the reach of children.
Keep away from sources of ignition - No smoking
Do not breathe vapors
In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
In case of accident or if you feel unwell, seek medical advice immediately (show the label if possible).
Use only in well-ventilated areas

For further information concerning safety, refer to Safety Data Sheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences, and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TELEFAX (+45) 56 64 00 90 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**