

Product Information:

Building Foam Extra 601

Sealing foam, isocyanate free, flexible and insulating**Product description & use:**

Building Foam Extra 601 is a new type of foam, totally without isocyanate, and based on the newest technology, which gives unique abilities:

- ▶ 0 % isocyanate – does not require epoxy certificate
- ▶ Permanently more elastic than traditional foam for sealing
- ▶ High thermal and acoustic insulation values

Building Foam Extra 601 has low post-expansion, and bonds to most building materials.

Is used for tightness and isolation around window- and doorframes, pipe outlets, in cavities, between elements of walls and more.

The product is registered in the database for construction products that can be included in the Nordic Ecolabelled construction.

**Physical / chemical data:****Uncured foam:**

Type:

1-component isocyanate free STP-foam

Shelf life:

12 months in unopened packing, if stored cool.

See production date on the can. The cans must always be stored in upright position.

Packaging:

| Item nr. | Colour | Size |
|----------|--------------|------------|
| 7631 | Light yellow | 500 ml can |

Cured foam:

Paintable:

Yes

Thermal conductivity:

0,033 W/m °C (DIN 52612)

Sound reduction index:

62 dB (EN ISO 10140)

Density:

Approximately 40 kg/m³

Resistance:

Can resist temperatures from -50 °C to +90 °C,

Sunlight (UV): Must be protected from sunlight



Directions for use:

Preparation:

The surfaces must be free of oil, grease, dirt, dust etc. Always make sure that the surfaces are humid before application of the foam, as it only cures in the presence of moisture.

Building Foam Extra 601 bonds to most materials, except from polyethylene, silicone and similar smooth surfaces.

Application:

Wear suitable gloves and eye/face protection. Remove the top and mount the valve grip with the already mounted hose. Be careful not to tighten the valve grip too hard, so that the valve isn't activated during mounting. Shake the can 15 – 20 times before use. The can is shaken continuously during use.

The can is used with valve facing down. The joint should only be filled approx. 50%, because the foam expands more during the curing. When used in larger joints it is recommended to apply water to the foam surface.

Application temperature:

Air and surface temperature 5 °C to 30 °C. Can temperature minimum +5 °C.

Yield:

The content of the can yields up to 8 litres of foam (free expansion)

Curing:

Building Foam Extra 601 is tack-free after 8 - 12 minutes and can be cut after approx. 45 – 60 minutes, at 20 °C and 60 % RH.

Treatment:

The foam must be protected against sunlight. After curing Building Foam Extra 601 can be painted with most paints and lacquers.

Cleaning:

Uncured foam can be removed with Pro Wipes 916 or acetone on a cloth.
Cured foam can only be removed mechanically.
Hands are washed with soap and water.

Health and safety:

For further information on safety, please refer to product safety datasheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK
PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75