

**Product Information:**

# Web Adhesive & -Filler Wet Room 218

**Waterproof adhesive and filler for fibre glass web & glass felt**

**General description and application:**

Web adhesive & -filler wet room 218 is used for mounting and filling fibre glass web & felt in wet rooms. It provides high covering ability and leaves a perfect basis for subsequent wet room painting.

The adhesive is also suitable for facades, which in combination with the felt is used as reinforcement to avoid the development of cracks.

The adhesive is pigmented and based on an acrylic dispersion and waterproof fillers. Therefore, this product has properties as an adhesive and filler/paint.



**Physical / chemical properties:**

**Adhesive:**

- Type: Acrylic dispersion
- Colour: white
- Consistency: Thixotropic
- Solids content: Approx. 61 %
- Density: Approx. 1,3 Kg/L
- Shelf life: Minimum 1 year in tightly closed packing if stored cool and dry. The product must be protected from freezing.

**Packaging:**

Item no	Size
4693	5 ltr. bucket



## Directions for use:

- Preparation:** *The foundation must be clean, dry, solid, non-smudging and free from wall-paper remnants.*
- On smudging or very absorbent surfaces priming should be done with Plaster Primer 224 or Plaster Primer Gel Extra 228 after cleaning.*
- Non-absorbent and painted foundations are sanded and washed with a cleaning agent.*
- The adhesive is stirred well before use.*
- Dilution:** *The adhesive is delivered ready for use but can if necessary be diluted with water.*
- Application temperature:** *10 °C – 30 °C, best at 20 °C.*
- Application:** *The adhesive is applied in an even layer to the wall, using brush, roller or spray application. The fibre glass web/ felt must be mounted while the adhesive is still wet.*
- If the adhesive is used as reinforcement, the adhesive should be applied in such a layer that the web is “drowned” in the adhesive.*
- Always follow the instructions of the wall covering supplier.**
- Yield:** *3 - 6 m<sup>2</sup>/ltr.*
- Drying time (20 °C, 60% RH):** *The adhesive is dry after approx. 1 hour. After 24 hours the fibre glass web/felt can be painted.*
- The adhesive is fully cured in 3 – 4 days.*
- Treatment:** *Further priming can be done when the adhesive is dry. Any swellings are cut up and glued.*
- The last treatment is done with a suitable paint with the desired gloss.*
- Mounted glass web/felt which is exposed to water and/or to the weather, must always be treated with an efficiently covering surface treatment.*
- Cleaning:** *Wash hands and skin with soap and water.*
- Remove stains and spots immediately with a damp cloth.*
- Clean tools with lukewarm water.*
- Dried adhesive can be removed mechanically or dissolved by soaking in water.*

## Health and safety:

*For further information on safety, please refer to product safety data sheet.*

*The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.*

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK**  
**PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**