

**Product Information:**

# Fire Guard PU Foam 587

**Fire retardant polyurethane foam****General description & application:**

Fire Guard PU Foam 587 is a fire retardant 1-component polyurethane foam for professional use.

The product has good adhesion and insulation properties.

Fire Guard PU Foam 587 is used for passive fire protections of linear joints around fire doors, windows and between concrete elements.

Fire Guard PU Foam 587 is tested according to EN 1366-4: 2006 + A1 2010, **linear joint seals**.

**Physical / chemical data:****Uncured foam:**

Type: 1-component polyurethane foam  
 Shelf life: 12 months in unopened packaging if stored cool and dry.  
 Production date can be found on the can. Stored standing in upright position.

**Packaging:**

Item no.	Colour	Size
7645	Red	750 ml can

**Cured foam:**

Paintable: Yes  
 Thermal conductivity: 0.04 W/m °C  
 Sound reduction index: 60 dB (EN ISO 10140)  
 Fire class: B1 (DIN 4102)  
 Temperatures: Can withstand temperatures from -50 °C to +90 °C at normal use.  
 Avoid direct sunlight (UV radiation)



## Directions for use:

- Dimensions:** See table 01 and 02 on page 3.
- Surface preparation:** The surfaces must be cleaned for oils, dirt and the like. Make sure to moist the surfaces before application of the foam, as curing is only occurring at the presence of moisture.
- Application:** Use gloves and safety glasses. Remove the safety cap and attach the valve grip with the plastic tube. The product is always used with the valve grip positioned downwards.
- Shake the can 20 times before use.
- The joint repair area is only filled partly as the foam expands 2 to 2½ times readily after application. The foam expands during mounting and curing, pressure from foam might cause flexible materials to deform.
- Application temperature:** +5 °C to +30 °C. Can must be at minimum +10°C. Ideal temperature is +20 °C.
- Yield:** The content of the can yields up to 5 meters joint (30 x 150 mm)
- Curing:** Fire Guard PU Foam 587 is tack free after approx. 15 minutes, and cuttable after 30 - 40 minutes, at 23 °C and 50 % relative humidity.
- After treatment:** Fire Guard PU Foam 587 must be protected against sunlight. The foam can be filled, papered or painted after curing.
- Cleaning:** Uncured foam can be removed with Pro Wipes 916 or acetone on a cloth. Cured foam can be removed mechanically.

## Health and safety:

For further information on safety, refer to the product safety datasheet.

Following joint constructions are tested according to EN 1366-4: 2006, linear joint seals. It is the responsibility of the user to clarify with relevant authorities that the product used are suitable for- and meets actual proposed task.

**Fire doors:**

Regarding installation of fire doors and windows, the manufacturers installation instructions must be followed at all times.

**Conditions for plasterboard walls:**

Gypsum plasterboard wall is a double-plasterboard construction according to EI60 requirements, double gypsum plasterboard on steel bars in total 120 mm thickness, insulated with mineral wool (50 kg/m<sup>3</sup>).

**Conditions for concrete walls:**

Concrete wall is 150 mm thick; concrete, lightweight aggregate concrete or brick.

**Conditions for applied wood:**

Wood with a density of minimum 450 kg/m<sup>3</sup>.

Table 01

Construction material	Thickness of wall (= joint depth)	Joint width	Fire class
Concrete/Concrete	150 mm	30 mm	EI30
Concrete/Plasterboard	120 mm	30 mm	EI30
Concrete/wood	150 mm	30 mm	EI30
Concrete/Steel	150 mm	30 mm	EI30
Concrete/Concrete	150 mm	15 mm	EI60
Concrete/Plasterboard	120 mm	15 mm	EI90
Concrete/wood	150 mm	15 mm	EI60
Concrete/Steel	150 mm	15 mm	EI45

Concrete/concrete, wall thickness variations

Table 02

Joint depth, mm	100	100	100	100	200	200	200	200
Joint width, mm	40	30	20	10	40	30	20	10
Fire Class	EI20	EI30	EI30	EI60	EI120	EI180	EI180	EI240

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK**

**PH. (+45) 56 64 00 70 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**